

Bohui GC1 Art Board

Item		Unit	Standards	Tolerance	Standard Substance					
Grammage		g/m²	GB/t451.2	±3%	210	230	250	270	300	350
Thickness		um	GB/t451.3	±15	263	308	343	370	413	483
		PT	USA	±0.6	10.4	12.1	13.5	14.6	16.3	19
Stiffness	MD	mN.m	GB/T22364	≥	5.2	7.5	12	14	16.3	23.5
	CD				2.5	3.5	6	6.5	8	11
Surface Roughness PPS10		um	ISO8791	<	1.2					
Folding Times			GB/T458		15					
Surface Strength		m/s	GB/T22365	≥	1.3					
Ply bond		J/m²	TAPPIT833	≥	130					
Brightness	TOP	%	GB/T7974	±3	90					
	Back	%		±3	85					
Gloss - TOP		%	GB/T8941	≥	50					
Moisture		%	GB/T462		6.0-8.0					
Testing condition:										
Temperature: (23±2) °C										
Relative Humidity: (50±2)										

Distributed by:

KPP-Antalis (Malaysia) Sdn Bhd

Level 3A, Wisma Comcorp,
 37, Jalan Pelukis U1/46, Section U1
 Temasya Industrial Park, 40150 Glenmarie Shah Alam
 Selangor Darul Ehsan

T +603 7627 8300 F +603 7627 6163

E info.my@kppantalis.com

