

# REFIT COTTON

## PRINTING AND FINISHING RECCOMENDATIONS

INKS	We suggest to print Refit with good quality duct fresh inks.
BLANKETS	For a good graphic impression, use compressible blankets.
PICKING	In case of slight dust due to the special composition of the paper, we suggest to wash frequently the rubber blankets.
SCREENS	For the offset printing process a screen value of 150 lpi is recommended. For dry offset printing this can be slightly higher, for example 200 lpi.
DRYING TIME	After printing, make small sheet pallets. For heavier graphic elements and higher densities, sufficient powder should be applied.
FINISHING	Prescoring is recommended for board weights and when folding against the grain direction. For higher board weights, we suggest to enlarge the size of the creasing rule.
DIGITAL PRINTING DRY TONER	Refit is suitable for dry toner digital printing.
DIGITAL PRINTING HP INDIGO	Refit is not yet suitable for HP Indigo printing.
HOT FOIL STAMPING	Good results have been achieved. We suggest to test different foils.
PRINTABILITY AND RUNNABILITY	Every method of printing, embossing, punching, die cutting, creasing, laminating and UV varnishing is possible. Due to the special composition of the paper, we suggest to test before printing.
NOTE	Due to its hygroscopic nature, paper can show curl issues if not conditioned properly. To avoid any issue, we recommend to store the paper closed in its original wrap inside the printing area for at least 24-48 hours. After this conditioning time, the wrapping can be open and the paper can be utilized.

# REFIT WOOL

## PRINTING AND FINISHING RECCOMENDATIONS

REFIT IS SUITABLE FOR SCREEN AND HOT FOIL PRINTING.

RUNNABILITY	Suitable for embossing, punching, die cutting, creasing and laminating.
NOTE	Due to its hygroscopic nature, paper can show curl issues if not conditioned properly. To avoid any issue, we recommend to store the paper closed in its original wrap inside the printing area for at least 24-48 hours. After this conditioning time, the wrapping can be open and the paper can be utilized.