

# REFIT COTTON

## TECHNICAL DATA

	METHOD		+/-	120 g/m <sup>2</sup>	200 g/m <sup>2</sup>	250 g/m <sup>2</sup>	360 g/m <sup>2</sup>
BASIC WEIGHT	ISO 536	g/m <sup>2</sup>	5%	120	200	250	360
THICKNESS	ISO 534	µm	5%	168	280	350	500
BULK	ISO 534	cm <sup>3</sup> /g	-	1,40	1,40	1,40	1,39
ROUGHNESS (BENDTSEN)	ISO 8791-2	ml/min	200	600	600	600	600

NB. At times slight differences may occur in paper shade, inclusions and look as a result of the use of natural raw materials.

# REFIT WOOL

## TECHNICAL DATA

	METHOD		+/-	120 g/m <sup>2</sup>	200 g/m <sup>2</sup>	250 g/m <sup>2</sup>	360 g/m <sup>2</sup>
BASIC WEIGHT	ISO 536	g/m <sup>2</sup>	5%	120	200	250	360
THICKNESS	ISO 534	µm	5%	175	300	370	510
BULK	ISO 534	cm <sup>3</sup> /g	-	1,46	1,50	1,48	1,42
MOISTURE CONTENT	ISO 287	%	1,0	6,0	6,0	6,0	6,5

NB. At times slight differences may occur in paper shade, inclusions and look as a result of the use of natural raw materials.