

Technical Data

THE FOLLOWING DATA REFER TO REMAKE

	Method		+/-	120 gsm	180 gsm	250 gsm	380 gsm	520 gsm
Basis weight	ISO 536	gsm	5%	120	180	250	380	520
Thickness	ISO 534	µm	6%	185	280	400	590	800
Bulk	ISO 534	cm³/g		1,54	1,56	1,60	1,55	1,54
Wax Pick test (Denninson)		N.	2	16	16	16	16	16
Cobb 60 sec	ISO 535	g/m²	5	30	35	40	40	40
Moisture content	ISO 287	%	0,5	6,5	6,5	6,5	7,0	7,0

THE FOLLOWING DATA REFER TO REMAKE CARAPACE

	Method		+/-	120 gsm	180 gsm	250 gsm
Basis weight	ISO 536	gsm	5%	120	180	250
Thickness	ISO 534	µm	10%	190	280	365
Bulk	ISO 534	cm³/g		1,58	1,56	1,46
Moisture content	ISO 287	%	0,5	6,5	6,5	6,5

NB. At times slight differences may occur in paper shade, inclusions and look as a result of the use of natural raw materials.