

BRISK TEXTURE GRANITE PURE WHITE

項 目		單位	120 g/m ²	140 g/m ²	170 g/m ²	200 g/m ²	240 g/m ²	290 g/m ²	測試方式
基重 Basis Weight		g/m ²	128±4%	148±4%	178±4%	208±4%	248±4%	298±4%	ISO 536
厚度 Thickness		μm	135±5%	160±5%	195±5%	230±5%	270±5%	330±5%	ISO 534
水份 Moisture Content		%	5.5±1	5.5±1	5.5±1	5.5±1	5.5±1	5.5±1	ISO 287
白度 Brightness		%ISO	95↑	95↑	95↑	95↑	95↑	95↑	ISO 2470
抗張強度 Tensile Strength	MD	kg/15mm	8.0 ↑	9.0 ↑	11.0 ↑	12.0 ↑	14.0 ↑	16.0 ↑	ISO 1924
	CD		4.5 ↑	6.0 ↑	7.0 ↑	8.0 ↑	9.0 ↑	9.5 ↑	
表面強度 Picking	W	A	≥10	≥10	≥10	≥10	≥10	≥10	T459
	F		≥10	≥10	≥10	≥10	≥10	≥10	
Note: The specification refers to an average of a composite sample according to our standard procedures.									
Not to be used for purposes other than what we specified. We reserve the right to modifications.									