

項 目		單位	250g/m ²	310g/m ²	370g/m ²	470g/m ²	測試方式	
基重 Basis Weight		g/m ²	250±10	310±10	370±10	470±10	ISO 536	
厚度 Thickness		μm	320±10	405±10	480±10	610±10	ISO 534	
剛挺度 Stiffness	MD	mN.m	≥7.0	≥15.0	≥23.0	≥38.0	ISO 2493	
	CD		≥3.5	≥9.0	≥13.0	≥22.0		
粗糙度 Roughness		T/B	μm	≤7.0	≤7.0	≤7.0	ISO 8791-4	
水份 Moisture Content		%	6.0±1.5				ISO 287	
白度 Brightness		%ISO	≥95				ISO 2469	
光澤度 75° Gloss		T/B	%	≤10				ISO 8254-1
表面強度 Picking		T/B	A	≥14				TAPPI 459
層間結合強度 Ply Bond		J/m2	≥150				TAPPI 569	

Note: The specification refers to an average of a composite sample according to our standard procedures.

Not to be used for purposes other than what we specified. We reserve the right to modifications.