

項 目		單位	250g/m ²	310g/m ²	370g/m ²	470g/m ²	測試方式
基重 Basis Weight		g/m ²	250±10	310±10	370±10	470±10	ISO 536
厚度 Thickness		μm	290±10	360±10	435±10	540±10	ISO 534
剛挺度 Stiffness	MD	mN.m	≥4.5	≥11.0	≥16.0	≥27.0	ISO 2493
	CD		≥2.5	≥6.0	≥9.5	≥15.0	
粗糙度 Roughness	T/B	μm	≤5.0	≤5.5	≤6.0	≤6.0	ISO 8791-4
水份 Moisture Content		%	6.0±1.5				ISO 287
白度 Brightness		%ISO	≥95				ISO 2469
光澤度 75° Gloss	T/B	%	≤10				ISO 8254-1
表面強度 Picking	T/B	A	≥14				TAPPI 459
層間結合強度 Ply Bond		J/m2	≥100				TAPPI 569
<i>Note: The specification refers to an average of a composite sample according to our standard procedures.</i> <i>Not to be used for purposes other than what we specified. We reserve the right to modifications.</i>							