



Oji Paper (Thailand) Ltd.

130-132 Sindhorn Building Tower II, 6th Floor,

Wireless Rd., Lumpini, Pathumwan, Bangkok 10330 Thailand.

Tel. (66-2) 263-2705, 263-3710 Fax : (66-2) 263-2701, 263-3701

Attn: Valued Customer

Quality Specification

Item	CB				CFB		CF				Method
	Black	Blue	Black	Blue	Black	Blue					
	56 gsm	56 gsm	80 gsm	80 gsm	50 gsm	50 gsm	51 gsm	56 gsm	82 gsm	130 gsm	
	White / Color	White / Color	White	White	White / Color	White / Color	White / Color	White / Color	White	White	
Basis Weight (g/m ²)	56.0 ± 4.0	56.0 ± 4.0	80.0 ± 4.0	80.0 ± 4.0	50.0 ± 4.0	50.0 ± 4.0	51.0 ± 4.0	56.0 ± 4.0	82.0 ± 4.0	125.0 ± 6.0	TAPPI 410
Thickness (µm)	72 ± 5	72 ± 5	105 ± 6	108 ± 6	63 ± 5	63 ± 5	64 ± 5	70 ± 5	102 ± 5	160 ± 7	TAPPI 411
Smoothness (Sec/10ml)	70 ± 50	70 ± 50	70 ± 50	70 ± 50	70 ± 50	70 ± 50	70 ± 50	70 ± 50	70 ± 50	70 ± 50	TAPPI 479
Moisture (%)	6.3 ± 0.5	6.8 ± 0.5	6.3 ± 0.5	6.3 ± 0.5	6.3 ± 0.5	6.3 ± 0.5	6.3 ± 0.5	6.3 ± 0.5	6.3 ± 0.5	6.3 ± 0.5	TAPPI 412
Brightness (%)	≥80 / -	≥80 / -	≥80	≥80	≥80 / -	≥80 / -	≥80 / -	≥80 / -	≥80	≥80	ISO 2470 (C/2°)
Curl	Flat~ -3	Flat~ -3	Flat~ -3	Flat~ -3	Flat~ -3	Flat~ -3	Flat~ -3	Flat ~ -3	Flat~ -3	Flat~ -3	
Product Validity*	5 years	5 years	5 years	5 years	5 years	5 years	5 years	5 years	5 years	5 years	

* Product Validity: The properly developed image on our “Phoenix” Carbonless Copy Paper can be read easily for at least 5 years, if stored under following conditions.

Temperature: 23 ± 5°C

Humidity : 50 ± 10%RH

Under dark place, avoiding direct sunlight.

Without contacting plastic such as vinyl chloride film.

Oji Paper (Thailand) Ltd.

Mr. Mitsuru Kobayashi
General Manager
Products Technology Div.

Issued on February 12, 2011