
PRINTING AND FINISHING RECCOMENDATIONS

Due to its content and the nature of 100% recycled fibres, SHIRO ECHO can be characterized by the presence of dots and by slight variations in shade.

INKS	To ensure good drying, Shiro Echo should be printed with fresh or semi-fresh inks; for heavier graphic elements, we recommend to use oxidizing inks.
BLANKETS	For a good graphic impression, use compressible blankets.
DRYING TIME	Drying times may vary according to the type of processing. For heavier graphic elements and higher densities, sufficient powder should be applied.
PRINTABILITY AND RUNNABILITY	Every method of printing, embossing, punching, die cutting, creasing, laminating, UV varnishing and silk screen is possible.
DIGITAL PRINTING	Suitable for digital printing. Not suitable for HP Indigo printing unless specifically stated.
NOTE	<p>Due to its hygroscopic nature, paper can show curl issues if not conditioned properly. To avoid any issue, we recommend to store the paper closed in its original wrap inside the printing area for at least 24-48 hours. After this conditioning time, the wrapping can be open and the paper can be utilized.</p> <p>For particular processes we recommend to carry out proofing trials, if required Favini's technical department remains available for any support.</p>

> Please contact our technical department for further suggestions.