

THE FOLLOWING DATA REFER TO SHIRO ECHO WHITE

	METHOD		+/-	80 g/m ²	90 g/m ²	100 g/m ²	120 g/m ²	140 g/m ²	160 g/m ²	200 g/m ²	250 g/m ²	300 g/m ²	350 g/m ²
BASIC WEIGHT	ISO 536	g/m ²	5%	80	90	100	120	140	160	200	250	300	350
THICKNESS	ISO 534	µm	5%	102	115	128	150	175	200	252	315	378	440
BULK	ISO 534	cm ² /g	-	1,28	1,28	1,28	1,25	1,25	1,25	1,26	1,26	1,26	1,26
CIE WHITENESS	ISO 11475	%	4	96	96	96	96	96	96	96	96	96	96
ROUGHNESS (BENDTSEN)	ISO 8791-2	ml/min	50	240	240	240	240	240	240	-	-	-	-
			150	-	-	-	-	-	-	500	500	500	500
OPACITY	ISO 2471	%	150	>88	>89	>91	>92	-	-	-	-	-	-
MOISTURE CONTENT	ISO 287	%	1,0	5,5	5,5	5,5	6,0	6,0	6,0	6,5	6,5	6,5	6,5

THE FOLLOWING DATA REFER TO SHIRO ECHO RAW SAND AND RAW GREY

	METHOD		+/-	120 g/m ²	200 g/m ²	250 g/m ²	350 g/m ²
BASIC WEIGHT	ISO 536	g/m ²	5%	120	200	250	350
THICKNESS	ISO 534	µm	5%	156	256	325	458
BULK	ISO 534	cm ² /g	-	1,30	1,28	1,30	1,31
ROUGHNESS (BENDTSEN)	ISO 8791-2	ml/min	150	500	700	-	-
			200	-	-	1000	1100
MOISTURE CONTENT	ISO 287	%	1,0	6,5	6,5	6,5	6,5

THE FOLLOWING DATA REFER TO SHIRO ECHO RAW BLACK

	METHOD		+/-	120 g/m ²	200 g/m ²	250 g/m ²	350 g/m ²
BASIC WEIGHT	ISO 536	g/m ²	5%	120	200	250	350
THICKNESS	ISO 534	µm	5%	160	260	330	463
BULK	ISO 534	cm ² /g	-	1,33	1,30	1,32	1,32
ROUGHNESS (BENDTSEN)	ISO 8791-2	ml/min	150	500	700	-	-
			200	-	-	1000	1100
MOISTURE CONTENT	ISO 287	%	1,0	6,5	6,5	6,5	6,5

NB. At times slight differences may occur in paper shade and look as a result of the use of recycled materials.