

KPP / signature

KPP Signature ES – Ultra fine paper and board range with a very smooth and velvety surface and a clear look-through. Made with FSC certified E.C.F. (Elemental Chlorine Free) pulp. Its characteristics provide perfect on-press performance, excellent ink yield and brilliant printed results. It is excellent for packaging and graphic materials such as labels, covers, inserts, deluxe brochures. It is particularly suitable for letterheads and writing papers. Suitable for offset pre-printing and subsequent printing on toner-based laser printers.

| SUBSTANCE | V.S.A. | OPACITY | ROUGHNESS | TENSILE STRENGTH | |
|------------------|--------------------|----------|--------------|------------------|-------------|
| ISO 536 | ISO 534 | ISO 2471 | ISO 8791 - 2 | ISO 8791 - 2 | |
| g/m ² | cm ³ /g | % | ml/min | long ± 10% | cross ± 10% |
| 100 ± 4% | 1,05 | 90 ± 2 | 70 ± 20 | 5,9 | 3,9 |
| 115 ± 4% | 1,05 | 92 ± 2 | 70 ± 20 | 7,2 | 4,2 |
| 140 ± 4% | 1,05 | 94 ± 2 | 70 ± 20 | 8,5 | 4,5 |
| 160 ± 5% | 1,05 | - | 70 ± 20 | 9,1 | 5,2 |
| 190 ± 5% | 1,05 | - | 70 ± 20 | 10,4 | 5,9 |
| 230 ± 5% | 1,05 | - | 60 ± 20 | 13,7 | 7,2 |
| 270 ± 5% | 1,05 | - | 60 ± 20 | 15 | 7,8 |
| 300 ± 5% | 1,05 | - | 60 ± 20 | 16,3 | 8,5 |
| 340 ± 5% | 1,05 | - | 60 ± 20 | - | - |

Brightness (col. Extra White) - ISO 2470 (R457) - 112% ± 2
Relative Humidity 50% ± 5 ref. TAPPI 502-98

Exclusively distributed by:

KPP-Antalis 