

KPP / signature

KPP Signature Laid is a ribbed texture paper and board in Premier white and Classic White. Produced with virgin ECF pulp coming from well managed forests, it is the perfect choice for corporate communication and creative applications such as greeting cards, brochures, publishing and deluxe editions.

PREMIER WHITE

Characteristic	Standard	Unit	100	120	220	Tolerance
Grammage	ISO 536	g/m ²	100	120	220	± 5%
Thickness	ISO 534	µm	133	160	304	± 5%
Bulk	ISO 534	cm ³ /g	1,33	1,33	1,33	-
Opacity	ISO 2471	%	>88	>89	-	-
Whiteness / CIE	ISO 11475	%	150	150	150	± 3
Cobb 60 sec FELT SIDE	ISO 535	g/m ²	35	35	35	± 5
Cobb 60 sec WIRE SIDE	ISO 535	g/m ²	35	35	35	± 5
Roughness FELT SIDE	ISO 8791-2	ml/min	800	800	1100	± 200
Roughness WIRE SIDE	ISO 8791-2	ml/min	500	500	900	± 200
Absolute Humidity	ISO 287	%	6,5	6,5	4,5	± 1,0

CLASSIC WHITE

Characteristic	Standard	Unit	100	120	220	Tolerance
Grammage	ISO 536	g/m ²	100	120	220	± 5%
Thickness	ISO 534	µm	133	160	304	± 5%
Bulk	ISO 534	cm ³ /g	1,33	1,33	1,33	-
Opacity	ISO 2471	%	>88	>89	-	-
Cobb 60 sec FELT SIDE	ISO 535	g/m ²	35	35	35	± 5
Cobb 60 sec WIRE SIDE	ISO 535	g/m ²	35	35	35	± 5
Roughness FELT SIDE	ISO 8791-2	ml/min	800	800	1100	± 200
Roughness WIRE SIDE	ISO 8791-2	ml/min	500	500	900	± 200
Absolute Humidity	ISO 287	%	6,5	6,5	4,5	± 1,0

Exclusively distributed by:

KPP-Antalis 

Document date: 1st June 2022